

# Overlay Paving

## Specification Advice

### PURPOSE

To transform your existing surface in a way that is efficient with stunning, long lasting results.

### WHERE

This specification is for areas where both regular and occasional vehicular traffic is expected. Perfect for driveways, pathways, balconies, emergency vehicle access areas, city centres, courtyards, schools, bridges and many more.

### WHY

By reusing your existing surface you save time, money and waste. Even cracked damaged surfaces can be overlaid with our flexible resin bound stone with no loose stone or delaminating.



# Notes – Overlay Paving

Movement joints should be allowed for every 20m and to reflect any on the surface below. Joints should also be used when overlaying different types and ages of surfaces. Cracks should be broken out if necessary and filled with a polymer/cement crack filling material.

Loose tiles or pavers should be removed or secured prior to StoneSet installation.

Areas that may be trafficked by heavy vehicles should have structural layers designed according to Australian standards.

The maximum deviation of the base should not exceed 10mm under a 3m straight edge.

Flow rates through StoneSet can reach 103ltrs/m<sup>2</sup>/second. Base preparation may need to vary depending on required porosity rates beneath the StoneSet layer. All non porous surfaces should be installed to required falls. The StoneSet layer can not be used to direct the flow of water.

Any new concrete should be allowed to fully cure. This is usually a period of 7 days depending on the mpa rating used. StoneSet can withstand heavy vehicular traffic such as delivery trucks with prior consultation.

The thickness of the sub-base layer required is dependent on sub-grade soil conditions. Total sub-base thickness will be dictated by expected loading and sub-grade strength. Particular attention should be given when clay rich soils are present. If plastic or silty sub-grade is present, then a capping layer should be used in accordance with Australian standards.

Expansion foam may be required along the edge if the area is enclosed between two concrete walls.

This specification is based on normal good practice for surfacing and does not absolve the specifier from designing a construction suitable for the expected traffic and ground conditions pertaining on a given site.

**The details in this specification are intended only as a guide in specifying StoneSet products, actual designs should be developed by the project designers taking into account the specific circumstances of the intended application. StoneSet assumes no responsibility for improper reliance upon or misuse of the data herein. Product design and specification are subject to change without further notice.**

For project specific advice please call **1300 392 155** or email [mail@stoneset.com.au](mailto:mail@stoneset.com.au)

 1300 392 155

